

Use of monolithic lithium disilicate for implant abutment and crown: a clinical report

> **N. MOBILIO¹, S. CATAPANO²**

Dental School, Dental Clinic, University of Ferrara, Ferrara, Italy
¹DDS - Assistant professor
²MD, DDS - Associate professor

DOI 10.23805 /JO.2019.11.03.06

ABSTRACT

Background Lithium disilicate is usually used for producing prosthetic crowns to be cemented on teeth or implant abutments. On the contrary, its use for producing implant abutment is not reported. This report describes the use of monolithic lithium disilicate to realize implant abutment and crown.

Case report A 60-year-old male patient required dental implant restoration for replacing the upper right central incisor. A lithium disilicate abutment and crown were realized by pressing.

Conclusion Lithium disilicate may be a valid alternative to zirconia for producing implant abutments in the esthetic area.

KEYWORD lithium disilicate; implant abutment; aesthetics.

INTRODUCTION

Lithium disilicate is an all-ceramic material that combines good mechanical properties and excellent aesthetic results. This ceramic is indicated for single crowns (1), veneers and inlays (2), may be pressed or milled, and it may be produced as a monolithic restoration or veneered for a highly esthetic outcome. Many *in vitro* studies evaluated both fracture resistance and adhesion on tooth structure of disilicate crown (3-5), and they are considered a reliable treatment

alternative even for posterior, high load-bearing areas (6). Lithium disilicate may also be used for single crowns cemented on titanium or zirconia implant abutments (7-9). On the contrary, lithium disilicate for producing implant abutments is not generally used. This report describes the use of monolithic lithium disilicate to realize an implant abutment and crown.

CASE REPORT

A 60-year-old male patient presented at the Prosthodontics Department of the University of Ferrara for the final restoration of a dental implant replacing the upper right central incisor (Thommen Medical). A temporary was adapted on the implant three months earlier and the peri-implant tissues were considered stabilized for finalization (Fig. 1). An impression was taken using customized coping (Fig. 2) (10).

A lithium disilicate abutment and crown (IPS e.Max Press, Ivoclar Vivadent AG) were realized by pressing (Fig. 3). The inner surface of the lithium disilicate abutment was etched by means of 5% hydrofluoric acid (IPS Ceramic gel, Ivoclar Vivadent AG) for 20 seconds, rinsed, cleaned in pure alcohol in an ultrasonic bath for ten minutes, treated with a universal primer (Monobond Plus, Ivoclar Vivadent AG) for 60 seconds and dried with hot air. The external surface of the titanium base was sandblasted and treated with the same primer. A composite cement (Multilink Hybrid Abutment, Ivoclar Vivadent AG) was mixed onto the inner surface of the abutment and then it was seated onto the titanium base until polymerization was achieved, carefully removing all the excess. The abutment was screwed on the implant with controlled torque (Fig. 4). The screw access hole was filled with polytetrafluoroethylene (PTFE). The lithium disilicate crown was luted on abutment following the same luting procedure and a quite similar cement (Multilink Automix, Ivoclar Vivadent AG) (Fig. 5). Transillumination showed a natural effect (Fig. 6). The follow-up at twelve months showed the stability of the result (Fig. 7).



FIG. 1. The temporary crown screwed on the implant.



FIG. 2. The impression coping modified according to the profile of the temporary crown.



FIG. 3. The lithium disilicate abutment and crown.



FIG. 4. The lithium disilicate abutment screwed on the implant.



FIG. 5. The lithium disilicate crown luted on the abutment.



FIG. 6. The lithium disilicate crown and abutment trans-illuminated.



FIG. 7 The 12-month follow-up.

DISCUSSION

Traditionally, implant abutments can be standard or customized. Customized abutments can be produced using various materials and techniques: they can be cast by gold or other metal or they can be milled by titanium or zirconia. A customized zirconia abutment may be entirely made by zirconia (including the connection) or it may be produced by cementing a zirconia abutment on a titanium base. This latter option has the advantage of connecting titanium on titanium, avoiding coupling materials with different biomechanical properties, which can produce complications (11-13). Using lithium

disilicate instead of zirconia on a titanium base presents some advantages: disilicate can be produced by both milling and pressing, being a material more versatile for the dental technician; it is more translucent than zirconia, producing a more natural final restoration; disilicate may be etched, increasing the adhesion to the composite cement used for luting. A technique to produce screw-retained implant crowns by lithium disilicate has been described (14), but the translucency of this material finds the best indication in esthetic rehabilitations.

CONCLUSIONS

In conclusion, using a lithium disilicate for producing implant abutment may be a valid alternative to zirconia in the esthetic area.

REFERENCES

1. Sorrentino R, Nagasawa Y, Infelise M, Bonadeo G, Ferrari M. In vitro analysis of the fracture resistance of CAD-CAM monolithic lithium disilicate molar crowns with different occlusal thickness. *J Osseointegr* 2018;10(2):50-56.
2. Denry I, Holloway JA. Ceramics for dental applications: A review. *Materials* 2010;3:351-68.
3. Zahran M, El-Mowafy O, Tam L, et al. Fracture strength and fatigue resistance of all-ceramic molar crowns manufactured with CAD/CAM technology. *J Prosthodont* 2008;17:370-7.
4. Guess PC, Zavanelli RA, Silva NR, et al. Monolithic CAD/CAM lithium disilicate versus veneered Y-TZP crowns: Comparison of failure modes and reliability after fatigue. *Int J Prosthodont* 2010;23:434-42.
5. Mobilio N, Fasiol A, Mollica F, Catapano S. Effect of different luting agents on the retention of lithium disilicate ceramic crowns. *Materials* 2015;8:1604-11.
6. Schultheis S, Strub JR, Gerds TA, Guess PC. Monolithic and bi-layer CAD/CAM lithium-disilicate versus metal-ceramic fixed dental prostheses: Comparison of fracture loads and failure modes after fatigue. *Clin Oral Investig* 2013;17:1407-13.
7. Joda T, Bürki A, Bethge S, et al. Stiffness, strength, and failure modes of implant-supported monolithic lithium disilicate crowns: Influence of titanium and zirconia abutments. *Int J Oral Maxillofac Implants* 2015;30:1272-79.
8. Weyhrauch M, Igiel C, Scheller H, et al. Fracture strength of monolithic all-ceramic crowns on titanium implant abutments. *Int J Oral Maxillofac Implants* 2016;31:304-9.
9. Mihali S, Canjau S, Bratu E, Wang HL. Utilization of ceramic inlays for sealing implant prostheses screw access holes: A case-control study. *Int J Oral Maxillofac Implants* 2016;31:1142-9.
10. Papadopoulos I, Pozidi G, Goussias H, Kourtis S. Transferring the emergence profile from the provisional to the final restoration. *J Esthet Restor Dent* 2014;26:154-61.
11. Klotz MW, Taylor TD, Goldberg AJ. Wear at the titanium-zirconia implant-abutment interface: A pilot study. *Int J Oral Maxillofac Implants* 2011;26:970-5.
12. Stimmelmayer M, Edelhoff D, Güth JF, et al. Wear at the titanium-titanium and the titanium-zirconia implant-abutment interface: A comparative in vitro study. *Dent Mater* 2012;28:1215-20.
13. Taylor TD, Klotz MW, Lawton RA. Titanium tattooing associated with zirconia implant abutments: A clinical report of two cases. *Int J Oral Maxillofac Implants* 2014;29:958-60.
14. Mobilio N, Catapano S. The use of monolithic lithium disilicate for posterior screw-retained implant crowns. *J Prosthet Dent* 2017;118:703-5.